

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4500	MPa	ISO 527
^[C] Stress at break	84	MPa	ISO 527
^[C] Strain at break	2.6	%	ISO 527
^[C] Charpy impact strength, +23°C	55	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1020	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Features

Long fiber reinforced

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Heat stabilized or stable to heat