

**Product Texts**

30% long strand glass fiber reinforced polypropylene. Black.

Flammability at thickness h (1 HB mm)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.3	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	5800	MPa	ISO 527
<sup>[C]</sup> Stress at break	92	MPa	ISO 527
<sup>[C]</sup> Strain at break	2.53	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	157	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.0	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1120	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Features**

Long fiber reinforced

**Regional Availability**

North America, Europe, Asia Pacific