

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6550	MPa	ISO 527
^[C] Stress at break	100	MPa	ISO 527
^[C] Strain at break	2.1	%	ISO 527
^[C] Charpy notched impact strength, +23°C	19	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	157	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1120	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Features
Long fiber reinforced

Delivery form
Pellets

Regional Availability
North America, Europe, Asia Pacific

Special Characteristics
U.V. stabilized or stable to weather