

CELSTRAN® PP-GF40-02 AF3001 NATURAL

PP-GLF40

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9330	MPa	ISO 527
^[C] Stress at break	149	MPa	ISO 527
^[C] Strain at break	2.3	%	ISO 527
^[C] Charpy notched impact strength, +23°C	46	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Characteristics**Delivery form**

Natural Color

Features

Long fiber reinforced