

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9200	MPa	ISO 527
^[C] Stress at break	130	MPa	ISO 527
^[C] Strain at break	2	%	ISO 527
^[C] Charpy impact strength, +23°C	62	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	60	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	25	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	30	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	158	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	135	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1210	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Coating, Transfer Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Features

Long fiber reinforced

Regional Availability

North America, Europe, Asia Pacific