

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	8964	MPa	ASTM D 638
Tensile Strength	121	MPa	ASTM D 638
Elongation at Break	2	%	ASTM D 638
Flexural Modulus	8274	MPa	ASTM D 790
Flexural Strength	179	MPa	ASTM D 790
Izod Impact notched, 1/8 in	267	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	908	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 264 psi	154	°C	ASTM D 648
Other properties			
Density	1210	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	260	°C	-
Mold temperature	60 - 80	°C	-

Characteristics

Processing

Injection Molding

Features

Long fiber reinforced

Delivery form

White

Regional Availability

North America, Europe, South and Central America

Special Characteristics

U.V. stabilized or stable to weather