

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	27	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Flexural modulus, 23°C	1750	MPa	ISO 178
Izod impact strength, +23°C	80	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
Shore D hardness	66	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Anti-static, High impact or impact modified, U.V. stabilized or stable to weather

Features

Low Warpage, Copolymer

Regional Availability

North America, Europe, South and Central America, Near East/Africa