

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 18 | g/10min | ASTM D 1238 |
| Temperature | 260 | °C | - |
| Load | 3.8 | kg | - |

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength at Yield | 53.1 | MPa | ASTM D 638 |
| Tensile Strength at Break | 41.4 | MPa | ASTM D 638 |
| Elongation at Break | 180 | % | ASTM D 638 |
| Flexural Modulus | 2068 | MPa | ASTM D 790 |
| Flexural Strength | 82.7 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 854 | J/m | ASTM D 256 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1240 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Features

Low Odor

Chemical Resistance

General Chemical Resistance

Regional Availability

North America