

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>14</b>	g/10min	ASTM D 1238
Temperature	<b>260</b>	°C	-
Load	<b>3.8</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>49</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>40</b>	MPa	ASTM D 638
Elongation at Break	<b>160</b>	%	ASTM D 638
Flexural Modulus	<b>1931</b>	MPa	ASTM D 790
Flexural Strength	<b>75.8</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>801</b>	J/m	ASTM D 256
<b>Other properties</b>			
Density	<b>1190</b>	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Special Characteristics

High impact or impact modified

#### Features

Low Odor

#### Regional Availability

North America