

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.008</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>60.7</b>	MPa	ASTM D 638
Elongation at Break	<b>110</b>	%	ASTM D 638
Flexural Modulus	<b>2340</b>	MPa	ASTM D 790
Flexural Strength	<b>89.6</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>800</b>	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	<b>130</b>	J/m	ASTM D 256
Temperature	<b>-20</b>	°C	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>98.3</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1210</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Delivery form

Pellets

### Special Characteristics

U.V. stabilized or stable to weather

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa