

Hybrid B3030

(PC+PBT)

Ravago Manufacturing Americas

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	32	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	5	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	63.4	MPa	ASTM D 638
Flexural Modulus	2480	MPa	ASTM D 790
Izod Impact notched, 1/8 in	690	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 264 psi	106	°C	ASTM D 648
Other properties			
Density	1210	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

General Purpose

Delivery form

Pellets

Regional Availability

North America