

Hybrid B6720

(PC+PBT)

Ravago Manufacturing Americas

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	3.8	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	48.3	MPa	ASTM D 638
Flexural Modulus	2070	MPa	ASTM D 790
Izod Impact notched, 1/8 in	690	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

General Purpose

Delivery form

Pellets

Regional Availability

North America