

Hostacom TRC 160N HF COCOA

PP-MX14

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	32	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	20	MPa	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Izod notched impact strength, +23°C	38	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	98	°C	ISO 75-1/-2
Other properties			
Density	1000	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Applications

Automotive

Features

Low Odor, Scratch Resistant, Copolymer

Regional Availability

North America