

**Product Texts**

Polypropylene copolymer, mineral filled, UV stabilised

Flammability @3.2mm nom. HB -  
thickn.  
Flammability @1.6mm nom. HB -  
thickn.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>1500</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>24</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>7</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>80</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>6.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Vicat softening temperature, B	<b>66</b>	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>980</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe, Asia Pacific, Near East/Africa