

Product Texts

Polypropylene, homopolymer, mineral filled, heat stabilized, low emission.

Flammability @3.2mm nom. HB -
thickn.
Flammability @1.6mm nom. HB -
thickn.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3500	MPa	ISO 527
^[C] Yield stress	29	MPa	ISO 527
^[C] Yield strain	3.2	%	ISO 527
^[C] Charpy impact strength, +23°C	25	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	2.6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	74	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1250	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Features

Low Emission, Homopolymer

Regional Availability

Europe, Asia Pacific, Near East/Africa