

Product Texts

Polypropylene, homopolymer, 20% mineral filled.

Flammability @3.2mm nom. thickn. HB -
 Flammability @1.6mm nom. thickn. HB -

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2600	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	3.2	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Vicat softening temperature, B	96	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1050	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific, Near East/Africa

Features

Homopolymer