

Product Texts

Polypropylene, homopolymer, mineral filled, high heat stabilization.

Flammability @3.2mm nom. thickn.	HB	-
Flammability @1.6mm nom. thickn.	HB	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3600	MPa	ISO 527
^[C] Charpy notched impact strength, +23°C	1.8	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Vicat softening temperature, B	93	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1250	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe, Asia Pacific, Near East/Africa