

POLYfill PPC B10075

PP-MX75

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Strength	17	MPa	ISO 527
Yield strain	5	%	ISO 527
Flexural modulus, 23°C	3000	MPa	ISO 178
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Vicat softening temperature, A	150	°C	ISO 306
Vicat softening temperature, B	87	°C	ISO 306
Glow Wire Ignition Temperature (GWIT)	750	°C	IEC 60695-2-13
GWIT - thickness tested (1)	2	mm	-
Other properties			
Density	2250	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

Europe, Asia Pacific

Delivery form

Granules