

**Vampter C 3528 V0**

(PC+PBT)-GF35

VAMP TECH SPA

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Izod impact strength, +23°C	<b>40</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>10</b>	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Flexural Modulus	<b>7000</b>	MPa	ASTM D 790
Flexural Strength	<b>120</b>	MPa	ASTM D 790

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>165</b>	°C	ASTM D 648
Vicat Temperature	<b>150</b>	°C	ASTM D 1525

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1540</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>90</b>	°C	-
Pre-drying - Time	<b>3</b>	h	-
Melt temperature	<b>260</b>	°C	-
Mold temperature	<b>70</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant, Halogen-free

**Features**

Low Smoke

**Certifications**

RoHS compliant

**Regional Availability**

Europe