

Product Texts

Polypropylene copolymer, 10% mineral filled, UV stabilised

Flammability @3.2mm nom. thickn.	HB	-
Flammability @1.6mm nom. thickn.	HB	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Vicat softening temperature, B	65	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	970	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Copolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe, Asia Pacific, Near East/Africa