

Product Texts

Base Polymer	Polypropylene Heterophasic Copolymer
Filler/Additive System	15 % talcum
Special Features	high heat stabilised
Market Segment	Automotive, building and construction
Application Area	interior decoration / finishing, gardening tools
Typical Applications	housings

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

^[C] Melt volume-flow rate, MVR	8	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties**Value****Unit****Test Standard****ISO Data**

^[C] Tensile Modulus	1900	MPa	ISO 527
^[C] Stress at break	15	MPa	ISO 527
^[C] Strain at break	50	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties**Value****Unit****Test Standard****ISO Data**

^[C] Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	68	°C	ISO 306

[C]: CAMPUS

Other properties**Value****Unit****Test Standard**

^[C] Density	1010	kg/m ³	ISO 1183
------------------------	-------------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Copolymer

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions in an air circulating dryer 80-120 °C
 for 2-4 h
 in a dry air (dessiccant) dryer 80-120 °C
 for 2-3 h
 dependant on moisture content

Processing Injection Moulding melt temperature 200-270 °C
 mould temperature 20-90 °C

Storage dry, protected from light