

POLIFOR® E25 TR/15 UV

PP-T15

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy impact strength, +23°C	91	kJ/m ²	ISO 179/1eU
^[C] : CAMPUS			

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 0.45 MPa	102	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	60	°C	ISO 306
^[C] : CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Density	1010	kg/m ³	ISO 1183
^[C] : CAMPUS			

Characteristics**Special Characteristics**

U.V. stabilized or stable to weather

Regional Availability

North America, South and Central America