

DOMOLEN PPCT20UV1 NC

PP-T20

DOMO Engineering Plastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2380	MPa	ISO 527
Yield stress	28	MPa	ISO 527
Yield strain	3.5	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy impact strength, +23°C	70	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	22	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4.1	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2.1	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	167	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	117	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Features

Copolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America, Europe, Asia Pacific