

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	19	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	1668	MPa	ASTM D 638
Tensile Strength	54	MPa	ASTM D 638
Elongation at Break	100	%	ASTM D 638
Flexural Modulus	2158	MPa	ASTM D 790
Flexural Strength	78.5	MPa	ASTM D 790
Izod Impact notched, 1/8 in	687	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	226	J/m	ASTM D 256
Temperature	-40	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	107	°C	ASTM D 648
DTUL @ 264 psi	86	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

High impact or impact modified

Features

Thermal Stability

Chemical Resistance

General Chemical Resistance

Regional Availability

Europe, Asia Pacific