

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	18	g/10min	ASTM D 1238
Temperature	260	°C	-
Load	3.8	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	51.7	MPa	ASTM D 638
Flexural Modulus	1931	MPa	ASTM D 790
Flexural Strength	75.8	MPa	ASTM D 790
Izod Impact notched, 1/8 in	694	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Low Odor

Chemical Resistance

General Chemical Resistance

Regional Availability

North America