

**HTC6060**

(PC+PET)

Shanghai Kumho Sunny Plastics Co., Ltd.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	260	°C	-
Load	5	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	265	°C	-
Load	5	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	56	MPa	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Strength	58	MPa	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Flexural Strength	70	MPa	ASTM D 790
Izod Impact notched, 1/8 in	750	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	115	°C	ISO 75-1/-2
Vicat softening temperature, B	130	°C	ISO 306
<b>ASTM Data</b>			
Vicat Temperature	137	°C	ASTM D 1525
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	1E15	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<b>Other properties</b>			
Density	1200	kg/m <sup>3</sup>	ISO 1183
Density	1200	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	110 - 120	°C	-
Pre-drying - Time	4 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	260 - 280	°C	-
Mold temperature	60 - 90	°C	-
Zone 1	230 - 250	°C	-
Zone 2	250 - 270	°C	-
Zone 3	260 - 280	°C	-
Nozzle temperature	260 - 280	°C	-
Screw speed	30 - 70	rpm	-
Back pressure	0.3 - 1	MPa	-

**Characteristics**

**HTC6060**

(PC+PET)

Shanghai Kumho Sunny Plastics Co., Ltd.

**Processing**

Injection Molding

**Applications**

Automotive, Electrical and Electronical

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Asia Pacific

**Chemical Resistance**

General Chemical Resistance