

INFINO AE-2130

(PC+PET)

Lotte Chemical Corporation

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 21 | g/10min | ISO 1133 |
| Temperature | 260 | °C | - |
| Load | 5 | kg | - |
| Molding shrinkage, parallel | 0.6 | % | ISO 294-4, 2577 |
| Molding shrinkage, normal | 0.6 | % | ISO 294-4, 2577 |
| ASTM Data | | | |
| Melt Flow Index, MFI | 21 | g/10min | ASTM D 1238 |
| Temperature | 260 | °C | - |
| Load | 5 | kg | - |
| Mold Shrinkage, MD | 0.0055 | mm/mm | ASTM D 955 |
| Mold Shrinkage, TD | 0.0055 | mm/mm | ASTM D 955 |
| Mechanical properties | | | |
| ISO Data | | | |
| Tensile Modulus | 2400 | MPa | ISO 527 |
| Yield stress | 56 | MPa | ISO 527 |
| Stress at break | 55 | MPa | ISO 527 |
| Strain at break | 90 | % | ISO 527 |
| Flexural modulus, 23°C | 2400 | MPa | ISO 178 |
| Flexural strength | 82 | MPa | ISO 178 |
| Charpy notched impact strength, +23°C | 33 | kJ/m ² | ISO 179/1eA |
| Izod notched impact strength, +23°C | 38 | kJ/m ² | ISO 180/1A |
| Rockwell hardness | R 111 | - | ISO 2039-2 |
| ASTM Data | | | |
| Tensile Modulus | 2300 | MPa | ASTM D 638 |
| Tensile Strength at Break | 56 | MPa | ASTM D 638 |
| Elongation at Break | 90 | % | ASTM D 638 |
| Flexural Modulus | 2500 | MPa | ASTM D 790 |
| Flexural Strength | 81 | MPa | ASTM D 790 |
| Rockwell Hardness | R 111 | - | ASTM D 785 |
| Izod Impact notched, 1/8 in | 550 | J/m | ASTM D 256 |
| Izod Impact notched, 1/4 in | 180 | J/m | ASTM D 256 |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 98 | °C | ISO 75-1/-2 |
| Temp. of deflection under load, 0.45 MPa | 120 | °C | ISO 75-1/-2 |
| Vicat softening temperature, B | 132 | °C | ISO 306 |
| ASTM Data | | | |
| DTUL @ 66 psi | 128 | °C | ASTM D 648 |
| DTUL @ 264 psi | 108 | °C | ASTM D 648 |
| Vicat Temperature | 132 | °C | ASTM D 1525 |
| Other properties | | | |
| Value | | | |
| Density | 1230 | kg/m ³ | ISO 1183 |
| Density | 1230 | kg/m ³ | ASTM D 792 |
| Processing Recommendation Injection Molding | | | |
| Value | | | |
| Pre-drying - Temperature | 110 | °C | - |
| Pre-drying - Time | 4 - 6 | h | - |
| Processing humidity | ≤0.02 | % | - |
| Melt temperature | 270 | °C | - |
| Mold temperature | 60 - 80 | °C | - |
| Zone 1 | 240 - 250 | °C | - |
| Zone 2 | 240 - 260 | °C | - |
| Zone 3 | 250 - 270 | °C | - |

INFINO AE-2130

(PC+PET)

Lotte Chemical Corporation

| | | | |
|--------------------|------------------|-----|---|
| Nozzle temperature | 250 - 270 | °C | - |
| Screw speed | 50 - 150 | rpm | - |
| Injection pressure | 98 | MPa | - |
| Back pressure | 0.5 - 2 | MPa | - |

Characteristics**Processing**

Injection Molding

Applications

Automotive

Delivery form

Pellets, Natural Color

Regional Availability

North America, Europe, Asia Pacific