

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--------------------------------------------|--------------|-------------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 20 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Flexural modulus, 23°C | 2100 | MPa | ISO 178 |
| Charpy notched impact strength, +23°C | 4 | kJ/m ² | ISO 179/1eA |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 0.45 MPa | 110 | °C | ISO 75-1/-2 |
| Other properties | | | |
| Density | 1050 | kg/m ³ | ISO 1183 |

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Features

Color Stability, Low Odor, Copolymer

Applications

Automotive

Regional Availability

Europe