

Lucent PP TPP-0310-20

PP-T20

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.012	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	33.1	MPa	ASTM D 638
Elongation at Break	10	%	ASTM D 638
Flexural Modulus	2206	MPa	ASTM D 790
Flexural Strength	51	MPa	ASTM D 790
Izod Impact notched, 1/8 in	26.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	76.7	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Characteristics**Features**

Homopolymer

Regional Availability

North America