

Meplen EH HTP20

PP-T20

Mepol S.r.l.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	32	MPa	ISO 527
Strain at break	20	%	ISO 527
Flexural modulus, 23°C	3800	MPa	ISO 178
Izod notched impact strength, +23°C	3.5	kJ/m ²	ISO 180/1A
Izod notched impact strength	2.8	kJ/m ²	ISO 180/1A
Temperature	0	°C	-
Shore D hardness	76	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	76	°C	ISO 75-1/-2
Vicat softening temperature, B	108	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Anti-static, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

Europe

Features

Homopolymer