

Network Polymers PP PPB 25 1202 TF20

PP-T20

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	13	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	23.1	MPa	ASTM D 638
Elongation at Yield	6.3	%	ASTM D 638
Flexural Modulus	1542	MPa	ASTM D 790
Izod Impact notched, 1/8 in	176	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	109	°C	ASTM D 648
Other properties			
Density	1060	kg/m ³	ASTM D 792

Characteristics**Features**

Copolymer

Regional Availability

North America