

Piolen® P T20ZH42

PP-T20

PiO Kunststoffe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	25	MPa	ISO 527
Stress at break	6.2	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	34	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	164	°C	ISO 11357-1/-3
Vicat softening temperature, A	164	°C	ISO 306
Vicat softening temperature, B	91	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Other properties			
Density	1040	kg/m ³	ISO 1183

Characteristics**Processing**

Other Extrusion

Delivery form

Natural Color

Special Characteristics

Anti-static

Features

Thermal Stability, Copolymer

Applications

Automotive

Regional Availability

Europe