

Product Texts

20% talc filled PP homo polymer compound

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	11	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2600	MPa	ISO 527
^[C] Yield stress	33	MPa	ISO 527
^[C] Yield strain	6	%	ISO 527
^[C] Charpy impact strength, +23°C	38	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	14	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	2	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	58	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	109	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	84	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
^[C] Burning rate, FMVSS, Thickness 1 mm	100	mm/min	ISO 3795 (FMVSS 302)

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1060	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	230 - 270	°C	-
Mold temperature	40 - 70	°C	-

Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Thermoforming

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Delivery form

Granules

Other text information

Injection molding

PREPROCESSING; Pretreatment

Predrying usually not necessary (2-4h / 80°C)

PROCESSING ;Processing:

Melttemperature	230 - 270	°C
Mouldtemperature	40 - 70	°C