

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Flexural Modulus	1725	MPa	ASTM D 790
Rockwell Hardness	R87	-	ASTM D 785
Izod Impact notched, 1/8 in	61.5	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	115	°C	ASTM D 648
DTUL @ 264 psi	66	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Features

Copolymer

Special Characteristics

High impact or impact modified

Regional Availability

North America