

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	27.6	MPa	ASTM D 638
Elongation at Yield	30	%	ASTM D 638
Flexural Modulus	1448	MPa	ASTM D 790
Rockwell Hardness	R90	-	ASTM D 785
Izod Impact notched, 1/8 in	320	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	113	°C	ASTM D 648
DTUL @ 264 psi	62.8	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America