

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	2200	MPa	ASTM D 790
Flexural Strength	40	MPa	ASTM D 790
Rockwell Hardness	R70	-	ASTM D 785
Izod Impact notched, 1/8 in	68.2	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	115	°C	ASTM D 648
DTUL @ 264 psi	65	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Features

Copolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America