

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.012	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Shore D hardness	73	-	ISO 7619-1
ASTM Data			
Tensile Strength	31	MPa	ASTM D 638
Elongation at Break	30	%	ASTM D 638
Flexural Modulus	2100	MPa	ASTM D 790
Flexural Strength	48	MPa	ASTM D 790
Izod Impact notched, 1/8 in	40	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	395	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
Coefficient of Thermal Expansion, MD	80	E-6/K	ASTM D 696
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	70	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	85 - 90	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	220 - 270	°C	-
Mold temperature	50 - 80	°C	-
Zone 1	195 - 215	°C	-
Zone 2	205 - 225	°C	-
Zone 3	215 - 235	°C	-
Screw speed	40 - 60	rpm	-
Injection pressure	60 - 140	MPa	-
Back pressure	0.1 - 0.5	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Features

Homopolymer

Regional Availability

Asia Pacific