

**Product Texts**

ECO compound

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1700	MPa	ISO 527
Yield stress	22	MPa	ISO 527
Yield strain	5	%	ISO 527
Flexural modulus, 23°C	1900	MPa	ISO 178
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	15	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Vicat softening temperature, B	60	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Low Emission, Low Odor, Scratch Resistant

**Applications**

Automotive

**Regional Availability**

Europe