

Product Texts

ECO compound

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	17	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1600	MPa	ISO 527
Tensile Strength	20	MPa	ISO 527
Yield strain	5	%	ISO 527
Flexural modulus, 23°C	1700	MPa	ISO 178
Charpy notched impact strength, +23°C	19	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	20	kJ/m ²	ISO 180/1A

Characteristics**Delivery form**

Black

Features

Copolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe