

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	17	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	30	MPa	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 4	h	-
Mold temperature	30 - 50	°C	-
Zone 1	220 - 260	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Features

Homopolymer