

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.7	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2700	MPa	ISO 527
Tensile Strength	33	MPa	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	160	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	125	°C	ISO 75-1/-2
Vicat softening temperature, B	155	°C	ISO 306
Other properties			
Density	1040	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Natural Color

Features

Homopolymer

Applications

General Purpose

Regional Availability

Europe