

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	35	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	21	MPa	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Izod notched impact strength, +23°C	50	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	8	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	63	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	115	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	1050	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Features

Copolymer

#### Delivery form

Pellets

#### Regional Availability

Europe

#### Special Characteristics

U.V. stabilized or stable to weather