

**Hifax BB 73 G C12719**

PP-T22

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	21	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	21	MPa	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Charpy notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	2.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-40	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1060	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Scratch Resistant, Copolymer

**Applications**

Automotive

**Regional Availability**

Europe