

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	22	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	17	MPa	ISO 527
Flexural modulus, 23°C	1600	MPa	ISO 178
Izod notched impact strength, +23°C	40	kJ/m ²	ISO 180/1A
Izod notched impact strength	5	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, B	45	°C	ISO 306
Other properties			
Density	1050	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe