

Hifax TRC 221X/1 BLACK

PP-T22

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Stress at break	16	MPa	ISO 527
Flexural modulus, 23°C	1500	MPa	ISO 178
Izod notched impact strength, +23°C	55	kJ/m ²	ISO 180/1A
Izod notched impact strength	8	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, B	45	°C	ISO 306
Other properties			
Density	1050	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Features

Copolymer

Applications

Automotive

Regional Availability

Europe