

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Strength	20	MPa	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Izod notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	110	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	1100	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Features

Copolymer

#### Delivery form

Pellets

#### Applications

Automotive

#### Special Characteristics

High impact or impact modified

#### Regional Availability

Europe