

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	3400	MPa	ISO 178
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
Izod notched impact strength	2	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	71	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	120	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Homopolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

Europe