

**Hostacom X 4305 LS71 BLACK**

PP-T22

LyondellBasell Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>18</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Melt flow index, MFI	<b>16</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>2200</b>	MPa	ISO 527
Yield stress	<b>27</b>	MPa	ISO 527
Yield strain	<b>5</b>	%	ISO 527
Charpy impact strength, +23°C	<b>65</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>4</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>60</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>107</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>74</b>	°C	ISO 306
<b>Other properties</b>			
Density	<b>1040</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Delivery form**

Pellets, Black

**Applications**

Automotive

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Regional Availability**

Europe