

Hostacom X 4305 LS71

PP-T22

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	16	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	27	MPa	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Other properties			
Density	1040	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Natural Color

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe