

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	19	MPa	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	20	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	62	°C	ISO 75-1/-2
Other properties			
Density	1050	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

Europe